

TEST REPORT

No.: SHIN1808055499ML

Date: Aug 03, 2018

Page: 1 of 2

CUSTOMER NAME: NANTONG YUANGE TRADING CO., LTD

ADDRESS: ROOM C, BUILDING 32, NO.299 KERUN ROAD, ANATONG, JIANGSU

The test results were transferred from report No.: SHIN1807052869ML dated: Jul. 31, 2018 issued by SGS.

Weight lifting barbell Sample Name

Material and Mark 2#: 60Si2Mn

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Test Required : Tensile Test, Hardness Test

Date of Receipt Jul 25, 2018 Jul 25, 2018 **Testing Start Date Testing End Date** : Jul 31, 2018

Test result(s) For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for SGS-CSTC Standards Technical Service (Shanghai)Co., Ltd.

Kelly Shi

Authorized signatory





TEST REPORT

No.: SHIN1808055499ML

Date: Aug 03, 2018

Page: 2 of 2

1. Tensile Test:

Test Method: ASTM A370-17a

Tool Mothod: No TM 7107 0 17 a										
Test item	Specimen type	Tensile strength (ksi)	Yield strength (0.2% offset) (ksi)	Elongation after fracture G =4D (%)	Reduction of area (%)					
Result-2#	Round specimen	184.0	161.6	17.5	37					

2. Hardness Test:

Test Method: ASTM E18-17e1

Test item	Sample	Test position	Result		
HRC	2#	Core	40.5	40.1	40.1



****** End of report******

